

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date
15 January 2004 (15.01.2004)

PCT

(10) International Publication Number
WO 2004/005183 A2

(51) International Patent Classification⁷:

C01B

(74) Agents: TANG, Henry et al.; Baker Botts L.L.P., 30 Rockefeller Plaza, New York, NY 10112-4498 (US).

(21) International Application Number:

PCT/US2003/003393

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 5 February 2003 (05.02.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:


PCT/US02/14539 7 May 2002 (07.05.2002) US

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Published:**

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR PREPARING NANOPARTICLES COMPRISING CERIUM OXIDE AND ZIRCONIUM



WO 2004/005183 A2

(57) **Abstract:** This invention provides a method for preparing nanoparticles comprising cerium oxide and zirconium and having a narrow size distribution. The method comprises providing a first aqueous solution comprising zirconium oxychloride and providing a second aqueous solution comprising a first component which is either cerium nitrate or hexamethylenetetramine. The second aqueous solution is added to the first aqueous solution to form a first mixture. A third aqueous solution comprising a second component which is either cerium nitrate or hexamethylenetetramine, and which is different from the first component, is added to the first mixture to form a second mixture. The second mixture is maintained at a temperature no higher than about 320 °K to form nanoparticles. The nanoparticles are then separated from the second mixture and sintered in air at a temperature ranging between about 500° and about 1100°C. The nanoparticles obtained by the method of the invention are at least in part crystalline.